

# Peroxidase Catalyzed Coupling Reaction of Phenolic Formulated Chitosan-Gelatin Based Nano Hydrogels Binding Domains For Enhance Cell Attachment

Shiv Prakash Mishra

Assistant Professor, Dept of Physics & Electronics  
Dr. Ram Manohar Lohia Avadh University, Ayodhya-224001, (U.P.), India

**Abstract-** *In enzymatically fabrication of phenolic chitosan (PC) and phenolic gelatin (PG) derivative with encapsulation of biphasic calcium phosphate (BCPNPs) and injectable nanocomposite hydrogels (INhydrogel) have much attention in biomedical applications for regenerating hard-soft tissues. Since enzymatic peroxidase catalyzed coupling reaction may proceed by phenolic formulated chitosan-gelatin based nanohydrogels as bonding domains due to free functional groups of gelatin and chitosan binding to –OH group in BCP resulting crosslinking density of IN hydrogels for enhanced cell attachment which indicating supporting effect on cell growth or migration of bioactive components of IN hydrogels. The formation of BCPNPs-encapsulated PG-PC IN hydrogel enhanced biomineralization in a phosphate buffer saline (PBS) at 37°C about pH 7.4 on the composite surface in the simulated biofluid which have significant in proliferation of bone marrow mesenchymal stem cells for typical bone cell regeneration in specific tissue engineering.*

**Keywords-** Gelatin, chitosan, injectable nanocomposite hydrogel, biphasic calcium phosphates.

## I. INTRODUCTION

Indeed, in unique chemistry of biological apatite ( $\text{Ca}_5(\text{PO}_4)_3 \text{X}$ ; where  $\text{X} = \text{F}$  or  $\text{OH}$ ) which is the main inorganic component of hard tissues such as bone and teeth<sup>1</sup>. The formation of hydroxyapatite ( $\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2$ ) crystals from octacalcium phosphate ( $\text{Ca}_8(\text{HPO}_4)_2(\text{PO}_4)_4 \cdot 5\text{H}_2\text{O}$ ) is well reported<sup>2,3</sup>. Including several other functional polymer used in artificial organs, tissue engineering, medical devices and dentistry etc<sup>4</sup>. Although, tyrosine based polyphosphates pertinent to potential biomaterial and polysaccharide (chitosan)-tripolyphosphate have attention<sup>5,6</sup>. Here, we have reported a newly enzyme mediated hydrogels which play an important role in biomedical and engineering application, due to their practical performance such as delivery of bioactive components treatment or replacement of damaged tissue, organs or regenerative typical tissue cells<sup>7</sup> and encapsulation of nanoparticles in order to enhance cell attachment and

osteoblast proliferation<sup>8</sup>. The hydrogels consist of hydrophilic polymers that swell in aqueous solution thus facilitating the transportation of substance such as nutrients and by-products from cell metabolism.

Although, the polysaccharides (chitosan, dextran, heparin and chondroitin sulphate) are playing an important role in preparation of injectable peroxidase enzyme mediated highly biocompatible and biodegradable hydrogels, that exhibited a great potential in tissue regeneration<sup>7,9</sup>. For hard tissue regeneration, the combination of mineral nanoparticles and the hydrogels has recently been a new trend in fabricating nanocomposite hydrogel for hard tissue substitutes such as dentistry, orthopedics and reconstructive surgery, which improved strength & mechanical properties<sup>10</sup>. The  $\beta$ -tricalcium phosphate dispersed hydrogels significantly improved the compressive strength and biomineralization in simulated body fluid. Although, the vancomycin-encapsulated nanocomposite hydrogel performed antimicrobial activity against *staphylococcus aureus*<sup>11</sup>. The nanocomposite hydrogels have also compatible with high adhesion density of mesenchymal stem/human cells<sup>12</sup>. It is well known that, the chitosan is tissue adhesive, hemostatic, anti-infective, biodegradable and supportive for cell attachment, but, however, not all cell types<sup>13,14</sup>. Collagen proteins and its denatured gelatin are also widely used for pharmaceutical and medical application due to their high biocompatibility, fast biodegradability and enhancement of cell attachment and proliferation<sup>15</sup>. The gelatin possesses more integrin binding domains for cell attachment and it enhances cell attachment as well as they are quickly degraded by collagenase (enzyme) within 3-4 days<sup>16</sup>. The calcium phosphate (CP) and biphasic (BCP) nanoparticles both have been used in orthopedic application because of its repairing, biocompatibility, osteoconductivity and osteointegration, with producing osteoinduction as compared to hydroxyapatite or  $\alpha$ -,  $\beta$ -tricalcium phosphate<sup>17</sup>.

In this paper we have reported the protein (gelatin) – polysaccharide (chitosan) based nanocomposite hydrogels are

prepared from 4-hydroxyl phenyl acetamide – conjugated – chitosan and tyramine or p-hydroxyl phenyl acetic acid (HPA) – functionalized gelatin in presence of BCPNPs, horseradish peroxidase (HRP) enzyme /H<sub>2</sub>O<sub>2</sub>. The chitosan /gelatin and BCPNPs - based IN hydrogels can be adjustable gelatin time, appropriate collagenase – mediated degradation rates and enhancement of biomineralization and bone cell growth that enable it to be a great platform for regenerative medicine to overcome some limitations of gelatin - chitosan based materials.




Fig.1- Chemical structure of chitosan and gelatin with synthetic scheme of PC-(a) and, PG Derivative (b).

## II. MATERIALS & METHODS

In experimental procedure, which are adapted from the work described by Nguyen et al<sup>8</sup>, where all the required chemicals and reagents are laboratory based standard. In preliminary, chitosan (1.0g) is dissolved in a solution of 40 ml distilled water and 0.5ml of 1M HCl. Then 4- hydroxyl-phenyl acetic acid (HPA) 0.45g was added into the mixture and pH of solution is adjusted to 5.0 and then 1-ethyle-3-(3-dimethylaminopropyl) carbodiimide (EDC) 0.90g is added to the chitosan solution under stirring for 24h (one day) at room temperature 25°C. The solution is dialyzed against distilled water using membrane dialysis, for 3 days to obtain PC. Now, gelatin (2.0g) and tyramine (1.0g) are dissolved in 30ml distilled water, with adjusted pH to 6, following addition of EDC Carbodiimide 0.50g under stirring for 24h. Then, the solution is dialyzed against deionized water using membrane dialysis for 3 days. Subsequently, the dialyzed solution is freeze and dried to obtain PG. In preparation of BCP

nanoparticles, the using of calcium chloride and tricalcium phosphate salts at molar ratio of Ca/P=1.57. The PH of the reaction mixture is maintained at pH 7. Calcination process is conducted at 750°C to obtain BCP nanoparticles, where the BCPNPs is obtained below 80nm in diameter by ball-milling process.

In preparation of gelatin or chitosan based hydrogels, the PG (40mg) is dissolved in distilled water (300µL) and it separated into two vials equally. Then enzyme HRP (30µL of 0.05mg/ml stock solution) and H<sub>2</sub>O<sub>2</sub> (30 µL of 0.05- 0.15% w/v stock solution) are added into each tube separately. The gelatin based hydrogel was formed by mixing two HRP & H<sub>2</sub>O<sub>2</sub> contained vials. Phenyl gelatin polymer concentration is 10% w/w in hydrogel. Chitosan based hydrogel is prepared by the same process as described for PG hydrogel, in which 8.0mg phenyl chitosan is prepared in (150µL) distilled water with HRP & H<sub>2</sub>O<sub>2</sub> as above mention. The final concentration of the polymers solution was 8% w/w. The gelatin time may determined by using the vial tilting method.

The PG-PC hydrogels formation have occurred when solution A (contained PG, PC and HRP) mixed with solution B (contained PG, PC and H<sub>2</sub>O<sub>2</sub>) at same volume of the precursor polymer solution as demonstrated in above experiment. Practically, BCPNPs encapsulating PG- PC hydrogels are prepared from the same hydrogels process, in which contained 10 w/w % of the BCPNPs. The gelatin time behaviours of the hydrogels and IN hydrogels are characterized at the different concentration of HRP and H<sub>2</sub>O<sub>2</sub> from 0.05- 0.15 to 0.20% wt/vol., with relatively that enzyme mediated hydrogels contained approximately 8 w/w % of the polymer concentration. The biodegradation of injectable nanocomposite hydrogels have been studied in a collagenase-mediated, in which these materials were immersed in phosphate buffer saline (PBS) solution pH 7.4 containing collagenase (0.2µg/ml) at 37°C and then monitoring their weight losses at different incubation times. Samples with different mass ratios having accurately weighted (wi) before immersing in 1ml of enzymatic solution. At the predetermined intervals, samples being removed from the incubation medium. Then, weight of remaining hydrogels and IN hydrogels (wt) is :

$$\text{Degradation rate (rate of weight loss \%)} = \frac{w_i - w_t}{w_i} \times 100$$

Where, w<sub>i</sub> & w<sub>t</sub> are initial or remaining weights of hydrogels/ IN hydrogels, respectively .

### III. RESULTS & DISCUSSION

Herein, the characterization study of polymers have reported that in crystalline phase of  $\beta$ -TCP & HAP with small particle size, the nanoparticles may be highly potential in fabrication of nanocomposite biomaterials. The study of HRP/ $H_2O_2$  mediated coupling reaction of phenolic moieties-modified polymer is an high efficiency to prepare injectable hydrogels<sup>7</sup> where the fast gelation time obtained to be 60s and 12s for preparation of (1:5wt/wt) PC and PG solution at around 0.125- 0.15 wt% of the used stock  $H_2O_2$  concentration, respectively, with molar ratio of  $H_2O_2$  and phenolic moiety to crosslinked polymer chains at 0.5 is optimal condition<sup>18</sup>. Generally PCD/PGD and IN hydrogels could be formed with in gelation time 40s. Figure-2 show that the representative data for gelation time(s) versus concentrate  $H_2O_2$  (wt %). The role of HRP enzyme which catalyzes to decompose  $H_2O_2$  in coupling phenolic or aniline derivatives for formulation and fabrication of several types of phenolic derivation based biomaterials as well as due to free function groups of gelatin and chitosan binding to -OH groups in BCP resulting in increasing crosslinking density of IN hydrogels, indicating supporting effect on cell growth and migration or sustainable release of bioactive components of these IN hydrogels<sup>18,19</sup>.




Fig.2 Representative Data for Gelation time Vs Concentration  $H_2O_2$  (wt%) of PG-PC Derivative and IN Hydrogel

The biodegradation and cellular compatibility behaviours of the gelatin or chitosan based biomaterials are partially different, where the collagenase induced degradation rate profiles that differently performed as changed mass ratios of PC-PG (1PC: 2.5PG and 1PC: 5PG) in the gels, approximately 60 wt/wt % of its weight at the end of this survey. The different behaviours could be derived from binding of calcium ions (released from BCPNPs) and collagenase leading to inhibition of its proteolytic activity<sup>20</sup>. Hence, such studies clarified that gelatin based materials have a fast biodegradable characteristics in a collagenase containing

media while the biodegradation of chitosan-formulated hydrogel could be modulated to enhance mineralization and implant for regenerating specific tissue.

Biom mineralization study indicated that, the PG-PC hydrogels and its nanocomposites sample are immersed in a PBS solution (pH 7.4) at 37°C. After 4 weeks (28 days) of incubation, soaking in the buffer solution, these materials have collected and washed with distilled water to remove soluble inorganic salts and then it characterized by SEM and other as X-ray diffraction method adapted. A highly crystallized phase of HAP encapsulated gelatin matrix could be observed which indicated a higher deposition of calcium and phosphate ion, which confirmed that the highly PG and PC formulated hydrogels samples performance in enhancing biom mineralization ability<sup>21</sup>. The study of gelatin enrich biomaterials have induce outgrowth of cells because gelatin owns more integrin binding domains for cell attachment and enhancing outgrowth of cells<sup>16,22</sup>. Resulting, it offers several different formulations of the PG-PC hydrogels /IN hydrogels with a various collagenase medicated degradation rate and the high cytocompatibility with mesenchymal stem cells. It because living cells are stained with green fluorescence by an intracellular esterase enzymatic reduction of a nonfluorescent calcein which enables implant with minimally invasive ways exhibiting its greatly potential for regenerating several kinds of typical tissues as combined with bioactive molecules, or/and nanoparticles such as growth factor, bioglass nanoparticles, genes and BCPNPs etc.

### IV. CONCLUSION

In present article, we have been reported the enzymatically fabricated phenolic protein (gelatin)-polysaccharide (chitosan) and encapsulation of biphasic calcium phosphate (BCP) nanoparticles encapsulated injectable nanocomposite hydrogels (INhydrogels) which were prepared from enzymatic peroxidase-catalyzed coupling reaction of phenolic formulated chitosan and gelatin based hydrogels which are as binding domains for enhances cell proliferation and cell attachment but the reaction depending on the amount of chitosan-gelatin formulated derivatives, where the IN hydrogels practically performed an appropriated biodegradation rate over a long period of time. Hence, these newly phenolic formulated gelatin-chitosan based encapsulated BCPNPs nanohydrogels biocomposite can enhance biom mineralization and proliferation on the composite surface. Regarding to these finding results with there osteoinduction, osteointegration and ostioconductivity characteristics of BCPNPs loaded phenolic gelatin and phenolic chitosan (PG-PC) derivative hydrogels to applying

practically as in bone cell regeneration under specific typical tissue engineering.

## REFERENCES

- [1] F.A. Cotton, G Wilkinson, C.A. Murillo and M.Bochmann, *Adv. Inorg. chem.*, John Wiley & Sons, Inc., edn. 6, (1999)
- [2] S.V. Dorozhkin, M.Epple, *Angew. Chem., Int. Ed.*41,3130,(2002)
- [3] T.Yokoi, T. Goto and S. Kitaoka, *Chem. Lett.*,48,855,(2019)
- [4] F.A.R.Mageed, M.M. Kareem and M. N. Al-Baiati, *Asian J. Chem*, 31,569,(2019)
- [5] A.S.Gupta and S.T.Lopina, *Polymer*, 46,2133,(2005)
- [6] A.Febriasari, D. Siswanta, N.Riyanto, N.H.Aprilita and F.Silvianti, *Asian J. Chem.*, 30,2509,(2018)
- [7] M.Kurisawa, J.E. Chung, Y.Y.Yang, S.J.Gao and H.Uyama, *Chem. Commun.*, 34,4312,(2005)
- [8] T.T.Nguyen, C.K.Huynh, V.T.Le, M.D.Truong, B.L.Giang, N.Q.Tran and M.T.Vu, *Asian J. Chem.*,31,1062,(2019)
- [9] L.S.M.Teixeira, S.Bijl, V.V.Pully, C.Otto, R.Jin, J.Feijen, C.A.van Blitterswijk, P.J.Dijkstra and M.Karperien, *Biomaterials*, 33,3164,(2012)
- [10] G.Tozzi, A.De Mori, A.Oliveira and M.Roldo, *Materials*,9,267,(2016)
- [11] J.A.Killion, L.M.Geever, D.M.Devine, C.L.Higginbotham and H.Farrell, *Int. J. Polym. Mater.Polym. Biomater.*, 63,641,(2014)
- [12] C.D.F.Moreira, S.M.Carvalho, H.S.Mansur and M.M.Pereira, *Mater. Sci. Eng. C*, 58,1207,(2016)
- [13] N.Q.Tran, Y.K.Joung, E.Lih, K.M.Park and K.D.Park, *Biomacromol.*, 11,617,(2010)
- [14] N.Q.Tran, Y.K.Joung, E.Lih, K.M.Park and K.D.Park, *Biomacromol.*, 12,2872,(2011)
- [15] S.Sakai, K.Hirose, K.Taguchi, Y.Ogushi and K.Kawakami, *Biomaterials*, 30,3371,(2009)
- [16] X.Liu, L.A.Smith, J.Hu and P.X.Ma, *Biomaterials*, 30,2252,(2009)
- [17] E.C.Victoria and F.D.Gnanam, *Trends Biomater. Artif. Organs*, 16,12,(2002)
- [18] D.H.Nguyen, N.Q.Tran and C.K.Nguyen, *J. Biomater. Sci.*, 24,1636,(2013)
- [19] D.Q.Ou, Y.X.Sun, X.D.Xu, S.X.Cheng, X.Z.Zhang and R.X.Zhuo, *Biomacromolecules*, 9,1155,(2008)
- [20] J.J.Robinson, *J. Cell. Biochem.*, 80,139,(2001)
- [21] Y.S.Wu, Y.H.Lee and H.C.Chang, *Mater.Sci.Eng.C*,29,237,(2009)
- [22] K.M.Park, K.S.Ko, Y.K.Joung, H.Shin and K.D.Park, *J.Mater. Chem.*, 21,13180,(2011)